

FIG. 1

09745880 122200




FIG. 2

00222T-08894260




FIG. 3

Penetration Depth vs. Ave. Amount Transferred (H1310 needle + 0g & 0.40g Add-on Spunbond Liner)




Fig. 4

002221" 0389460

Unexpected Viscosity Synergy From Combination of Clay and Organoclay




Fig. 5

Rheological Synergy From Combination of Fumed Silica and Clays




Fig. 6